



Head Office
 Red Deer, Alberta
 Phone: 403-314-2221
 Fax: 403-314-2226
 Web Site: www.hpc.ca

1250 Rust Guard Grey Primer

Material Description

A fast drying, non-lifting, anticorrosive primer, offering protection in mild to moderately corrosive atmospheres.

Intended Applications

For use on Structural steel, plate stock, tanks, and iron. May be top coated with SPEED or INDUSTRIAL Enamel.

Colors Available	Finish
Grey	Low Sheen

Physical Properties

Resin System	Pigment System
Phenolic Modified alkyd	Titanium dioxide, Carbon black, and Yellow oxide

Solvent System	Packaged Viscosity
Aliphatic and aromatic hydrocarbons	7 +/- 0.5 Poise @25C

Solids by Weight	Solids by Volume
56.8 +/- 2%	38.1 +/- 2%

Theoretical Coverage	Total VOC
164.0 sq ft/L	521 g/L

Wet Film Thickness	Dry Film Thickness	Specific Gravity
2.6 - 3.9 mils	1.0 - 1.5 mils	1.207

Dry to Touch *	Dry to Handle *	Dry to Recoat *
30 minutes	6 hours	30 minutes

Coats Required	Components	Pot Life Hours
1-2	1	N/A

Recommended Thinners	Use With
Xylene or TS-28 Slow Reducer	5000 and 8000 series enamels

Additional Application Notes

* Times listed are at 25°C. Temperature and humidity will affect dry and recoat times.



Head Office
 Red Deer, Alberta
 Phone: 403-314-2221
 Fax: 403-314-2226
 Web Site: www.hpc.ca

1250 Rust Guard Grey Primer

Required Surface Preparation and Application Parameters

Surface Preparation	Surfaces must be free of dirt, grease, and oil. Steel surfaces must be thoroughly cleaned and preferably sandblasted to a SSPC-6 commercial blast.		
Atmospheric Conditions	Surface and product temperatures must be at least 10 deg C (50 F) and at least 3 deg C (5F) above dew point. Apply in dry weather when relative humidity is less than 85%.		
Blend Ratio	N/A		Induction Period
Reduction	Airless (5-10%) / A.A. Airless (10-20%)		
Application Viscosity	Airless (28" Z #2) / A.A. Airless (24" Z #2)		
Force Cure	15 min flashoff followed by a 30 minute force at 60 degrees celsius		
Airless Pressure	1400-2000 PSI min at tip	Airless Tip Size	0.009" - 0.013"
AA Airless Pressure	850 PSI min at tip	AA Airless Tip Size	0.009" - 0.013"
AA Airless Air Pressure	30 - 60 PSI		
Conventional Spray			
Brush	N/A	Roller	N/A
Procedure Part 1	Rinse all equipment with thinner prior to and immediately following application.		
Procedure Part 2	When application is made by airless or air assisted airless, use and inbound pressure approx. 10-15 lbs above the level at which "fingering"		
Procedure Part 3	Special attention should be given to all edges, pits, welds, corners, rivets and other rough spots to insure complete coverage.		

Additional Information

Package Sizes	3.78 litre, 18.9 litres, 205 litres
Safety Information	See label precautions and MSDS.

Date Issued 20/04/2004 Supersedes new issue

The above information is given in good faith and to the best of our knowledge. Every reasonable precaution is taken in the manufacture of all products and compilation of data to ensure that they are consistent with the Manufacturer's standards. As the effectiveness of each product depends, in part, on correct methods of use and application, and since the conditions of the surface, application and method of use are beyond our control, no guarantee of such products or this data is made or implied by this. By virtue of this disclosure, it is the responsibility of the buyer to satisfy itself of the suitability of the goods for its own particular process and it will be deemed to have done so by virtue of accepting the goods on this understanding.